



**TECHNICAL DATA
80/20 BLEND FILTRATION MEDIA**

MATERIAL DESCRIPTION A low energy heavy-duty air medium, with polyester enhanced dimensional stability and structural integrity. This media has outstanding resistance to moisture and humidity.

Frazier Permeability
(CFM/sqft @ 0.5 in. w.g): 14

Test Flow Rate: 460 CFM

Initial Resistance: 0.45 in. w.g.

Final Resistance: 4.0" in. w.g.

Test Dust: SAE Fine

Test Dust Feed Rate: 2.0 g/1000
cu.ft.

Dry Mullen Burst: 40 psi

Equivalent BIA Rating: U,S,G, & C

Particle Removal Efficiency

0.3 – 0.4	97.35%
0.4 – 0.5	98.07%
0.5 – 0.6	98.63%
0.6 – 0.8	98.83%
0.8 – 1.0	99.17%
1.0 – 1.5	99.24%
1.5 – 2.0	99.15%
2.0 – 3.0	99.17%

We have the pulse of the Industry so the choice is yours!