



**TECHNICAL DATA
CELLULOSE FILTRATION MEDIA**

MATERIAL DESCRIPTION A heavy duty air medium with excellent capacity ratio. This media has excellent resistance to moisture and humidity.

	Typical Values	Metric Equivalent
Basis Weight (pounds per 3,000 sqft.)	78	129 g/m ²
Caliper (overall, in inches)	.029	0.74 mm
Corrugation depth (in inches)	.016	0.41 mm
Frazier Permeability (CFM/sqft @ 0.5 in. w.g.)	18	144 (L/sec./m ² @)P 20)
First Bubble Point (inches w.g.) (microns)	7.1 (I) 53.5	180 mm 53.5
Mullen Burst psi As is dry As is wet	53 25	365 kPa 172 kPa
Resin Content (%)	18	18
Volatiles (%)	4.3	4.3

All test values are Off Machine (Unconditioned).
Data are taken from production runs to show “typical” properties.

We have the pulse of the Industry so the choice is yours!